

## Reference Numbers for 008716 USA/CPS/IBSS/LAP

substrate	104
chamber	106
process zone	109
gas delivery system	112
substrate support	114
gas energizer	116
chamber enclosure walls	118
shields	120
upper shield section	120a
lower shield section	120b
gas exhaust	122
target	124
cover ring	126
deposition ring	128
support ring	130
insulator ring	132
shutter disk	133
surface of substrate support	134
coil	135
coil support	137
clamp shield	141
sidewalls	164
bottom wall	166
ceiling	168
electrode	170
electrode power supply	172
gas sources	174
conduit	176
gas flow control valve	178
gas distributor	180
gas outlets	182
exhaust port	184
exhaust conduit	186
throttle valve	188
exhaust pumps	190
target power supply	192
component	300
coating	302
overlying coating	302
first metal layer	302a
second metal layer	302b
component underlying structure	304
upper surface of structure	306
surface of coating	308
intermetallic compounds	310
cracks and crevices	311
solid blasting beads	312

## ATTACHMENT A

AMAT DOCKET NO: 008716 USA/CPS/IBSS/LAP

TITLE: CLEANING AND REFURBISHING CHAMBER COMPONENTS HAVING METAL COATINGS

INVENTOR(S): Yixing Lin, Dajiang Xu, Clifford Stow

FILING DATE: October 17, 2003

KEY WORDS: process chamber component, metal coating, refurbish, bead blasting

### ABSTRACT:

A component of a process chamber is refurbished and cleaned to remove an intermetallic compound from the component. The component has a structure having a coating that includes a first metal layer over the intermetallic compound. To refurbish the component, the first metal layer is removed to form an exposed surface that at least partially includes the intermetallic compound. The exposed surface is bead blasted in a penetrative bead blasting step by propelling blasting beads having a bead diameter of less than about 180 micrometers with a gas that is pressurized to a pressure of less than about 310 kPa (45 psi), towards the exposed surface, thereby removing the intermetallic compound from the exposed surface of the structure to form a cleaned surface. A second metal layer is then formed over the cleaned surface.

### DRAWING:




Figure 1a




Figure 1b




Figure 1c

### CLAIM:

1. A method of refurbishing a component of a process chamber, the component comprising a structure having a coating comprising a first metal layer over an intermetallic compound, the method comprising:
  - (a) removing the first metal layer to form an exposed surface that at least partially comprises the intermetallic compound;
  - (b) performing a penetrative bead blasting step by propelling blasting beads having a bead diameter of less than about 180 micrometers with a gas that is pressurized to a pressure of less than about 310 kPa towards the exposed surface, thereby removing the intermetallic compound from the exposed surface of the structure to form a cleaned surface; and
  - (c) forming a second metal layer over the cleaned surface.